

UHMWPE
YUHW HIDDEN U050 H

Features and Uses

Application	U(V)HMWPE / UHMWPE (UHMWPE)
Features	Ultra High Impact Strength, Excellent Processibility, High Wear Resistance
Uses	Products required high impact strength, Diverse Application (Compression Molding, Ram Extrusion. etc)

Properties

Items	Specification	Unit	Test Method
Average Mv (10^6 g/mol)	3.7	-	KPIC Method
Density	0.93	g/cm ³	ASTM D1505
Bulk Density	0.46	g/cm ³	ISO 60
Avg. Particle Size	125	μm	KPIC Method
Tensile Strength at Yield	>170	kg/cm ²	ASTM D638
Elongation at Break	>300	%	ASTM D638
Hardness	60	Shore D	ASTM D2240
Impact Strength (Izod with Notch)	No Break	kg _f cm/cm	ASTM D256
Charpy Impact Strength (Double Notched)	200	kJ/m ²	ISO 11542-2
Abrasion Resistance	105	U050=100	ISO 15527
Melting Point	133	°C	ASTM D3418

※ Above data are intended to serve as guides only, and are not sales specification limits.

Contact Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0847	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr