

UHMWPE
YUHWA HIDDEN U090L H

Features and Uses

Application	U(V)HMWPE / UHMWPE (UHMWPE)
Features	Higher wear resistance than U070 H, Large particle size
Uses	Compression Molding, Ram Extrusion

Properties

Items	Specification	Unit	Test Method
Average Mv (10^6 g/mol)	9	10^6 g/mol	KPIC Method
Density	0.93	g/cm ³	ASTM D1505
Bulk Density	0.46	g/cm ³	ISO 60
Avg. Particle Size	190	μm	KPIC Method
Tensile Strength at Yield	>170	kg/cm ²	ASTM D638
Elongation at Break	>300	%	ASTM D638
Hardness	59	Shore D	ASTM D2240
Impact Strength (Izod with Notch)	No Break	kg _r cm/cm	ASTM D256
Charpy Impact Strength (Double Notched)	110	kJ/m ²	ISO 11542-2
Abrasion Resistance	80	U050=100	ISO 15527
Melting Point	133	°C	ASTM D3418

※ Above data are intended to serve as guides only, and are not sales specification limits.

Contact Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0847	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr